

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (currently amended): A porous fiber comprising a hydrophobic solvent-soluble polymer and an organic compound having a plurality of hydroxyl groups, and having an average fiber diameter of 0.1-20  $\mu\text{m}$  and a void percentage of at least 5%, and

wherein the number-average molecular weight of the organic compound having a plurality of hydroxyl groups is not less than 62 nor more than 300.

2. (original): The porous fiber according to Claim 1, wherein the hydrophobic solvent is a halogen element-containing hydrocarbon.

3. (original): The porous fiber according to Claim 2, wherein the halogen element-containing hydrocarbon is selected from the group consisting of methylene chloride, chloroform, dichloroethane, tetrachloroethane, trichloroethane, dibromomethane, and bromoform.

4. (original): The porous fiber according to Claim 1, wherein the hydrophobic solvent-soluble polymer is selected from the group consisting of polylactic acid, polycaprolactone, polycarbonates, polystyrene, and polyarylates.

5. (cancelled).

6. (currently amended): A fiber structure comprising porous fibers that comprise a hydrophobic solvent-soluble polymer and an organic compound having a plurality of hydroxyl groups, and have an average fiber diameter of 0.1-20  $\mu\text{m}$  and a void percentage of at least 5%,  
and

wherein the number-average molecular weight of the organic compound having a plurality of hydroxyl groups is not less than 62 nor more than 300.

7. (original): The fiber structure according to Claim 6, wherein the hydrophobic solvent is a halogen element-containing hydrocarbon.

8. (original): The fiber structure according to Claim 7, wherein the halogen element-containing hydrocarbon is selected from the group consisting of methylene chloride, chloroform, dichloroethane, tetrachloroethane, trichloroethane, dibromomethane, and bromoform.

9. (cancelled).

10. (original): The fiber structure according to Claim 6, wherein the hydrophobic solvent-soluble polymer is selected from the group consisting of polylactic acid, polycaprolactone, polycarbonates, polystyrene, and polyarylates.

11. (withdrawn - currently amended): A method for producing a fiber structure according to claim 1, comprising porous fibers that have an average fiber diameter of 0.1-20  $\mu\text{m}$  and a void percentage of at least 5%, and wherein the number-average molecular weight of the

organic compound having a plurality of hydroxyl groups is not less than 62 nor more than 300,  
including a step in which a solution is produced by dissolving a hydrophobic solvent-soluble  
polymer and an organic compound having a plurality of hydroxyl groups in a hydrophobic  
solvent, a step in which the solution is spun by electrospinning, and a step in which a fiber  
structure accumulated on a collector is obtained.

12. (withdrawn): The method for producing the fiber structure according to Claim 11,  
wherein the hydrophobic solvent is a halogen element-containing hydrocarbon.

13. (withdrawn): The method for producing the fiber structure according to Claim 12,  
wherein the halogen element-containing hydrocarbon is selected from the group consisting of  
methylene chloride, chloroform, dichloroethane, tetrachloroethane, trichloroethane,  
dibromomethane, and bromoform.